



Product:	MASTERNET R-90 10x10 Fiberglass mesh
Supplier:	MASTERPLAST Kft., 8143 Sárszentmihály, Árpád u. 1/a. (www.masterplastgroup.com)
Size, packaging:	1 m*50 m = 50 sqm/roll
Application:	Proper for the reinforcement of traditional plasters, while increasing their strength and reducing the extent of shrinkage cracks.
Material:	"C" glass with alkali-resistant treatment

Properties	Relevant standards	Technical data
Length	Manufacturer's declared value (MDV)	50 m (±1 %)
Width	MDV	100 cm (±1 %)
Square dimension	MDV	10*10 mm
Treated fabric weight	MDV	90 g/m ² (±5%)
Loss of ignition	MDV	17% (±2%)
Tensile strength (warp/weft)	EN 13496	1650 N/5 cm / 650 N/5 cm
Elongation (warp/weft)	EN 13496	2,0-3,0% / 2,0-3,0%
Tensile strength after aging (warp/weft)	EN 13496	900 N/5 cm / 450 N/5 cm
Elongation (warp/weft)	EN 13496	2,0-3,0% / 2,0-3,0%
Reaction to fire	EN 13501-1	NPD

Storage and handling

Packed rolls are to be stored in dry rooms, protect against UV and heat, practically packed in plastic foil, vertically in cardboard box, on a wooden pallet. The temperature of storing shall be between (-)10°C and (+)40°C.

Guarantee, warranty

In accordance with the current legislations and the conditions of the distributor. The observation of the application rules of the product and presentation of the invoice constitute a prerequisite for possible future warranty claims.

Health and safety

No labelling required in accordance with the relevant regulation (EC) No. 1907/2006 of the European Parliament and of the Council.

This datasheet corresponds to our current knowledge, experiences and general informations on the subject, but may be revised as new knowledge and/or experience becomes available. It does not imply any legally binding assurance. The product possesses the given technical characteristics. Since all variations of end-using of the product can not be anticipated, the designer/end-user's responsibility to make sure of the suitability of this product for particular purposes, structures.

This technical datasheet is applied to products sold by Masterplast Kft. and valid until withdrawal or until modification. Since this datasheet may be subject to revision, it is the responsibility of designer/end-user to make sure of possessing the latest version of the datasheet (*see date of issuing). Most recent version of this datasheet can be also accessed under www.masterplastgroup.com. Modification of the technical datasheet repeals the previously issued versions!